



M113

Chopped Strand Mat for Hand-Lay Up

PRODUCT DESCRIPTION

This product is produced using Advantex[®] glass fiber. Advantex[®] glass fiber combines the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass.

The M113 chopped strand mat is made with low size strands of Advantex[®] Glass Roving, held together by a powder binder which is extremely soluble in styrene.

The basic strand has a sizing system containing a silane coupling agent. This multi-purpose mat is used in numerous applications; this explains the extensive range of weights and widths available.

PRODUCT REFERENCE

Example : M113 300-130 1B

M113 : OCVTM Reinforcements code for this chopped strand mat

300 : roll weight (g/m²)

130 : roll width (cm)

1B : number of trimmed edges (zero, one or two)



PRODUCT APPLICATION

- Good surface appearance
- Continuous laminating (translucent panels, exterior panels for truck trailers, sandwich panels, etc..)
- Anti-corrosion applications.

FEATURES AND PRODUCT BENEFITS

- Excellent compatibility with polyester resins, producing laminates with very high clarity (without any appearance of the strand pattern)
- Very high smoothness of the laminate surface with no visible strands
- Excellent compatibility with vinylester and epoxy resins.
- Approved by Lloyd's Register
- Approved by Det Norske Veritas

TECHNICAL CHARACTERISTICS (NOMINAL VALUES)

WEIGHT (G/M ²)	LOSS ON IGNITION (%)	MOISTURE (%)
ISO 1889	ISO 1887	ISO 3344
100 ± 16%	10.5 ± 40%	0.2
150 ± 16%	8 ± 40%	
300 ± 16%	4.5 ± 40%	
450 ± 16%	3.5 ± 40%	
600 ± 16%	3.2 ± 40%	

VISUAL CHARACTERISTICS OR POSSIBLE DEFECTS

- Unbound edges
- Holes (> 40mm) or tears
- Dirt spots (greater than 5 mm)
- Unopened strands
- Accumulation of fibers (>40mm)

Each 100 m² roll of chopped strand mat section may contain at most 6 of the defects listed above.

M113

Chopped Strand Mat for Hand-Lay Up

PRODUCT AVAILABILITY

All range of widths (between 10 and 320 cm) and weights are available. Most combinations of weights and widths can be supplied (may be subject to minimum order quantities, extended lead times and complementary widths).

STANDARD WEIGHT (G/M ²)	STANDARD WIDTH (CM)	DIAMETER (CM)	LENGTH	WEIGHT (KG)
300	130/125	40	220	86
450			150	88
600			110	86

A roll is considered to be complete if it measures more than 70% of the nominal length.

PACKAGING

- Each roll is wound up on a cardboard tube (internal diameter 101 mm) and packaged in an individual cardboard box, 40 x 40 (L x W); the height is equal to the width of the mat. Nine standard rolls are packed vertically on a pallet, secured by shrink-wrap polythene. The pallet is wrapped with polyamide straps.

MAT WIDTH	PALLET DIMENSIONS	NET PALLET WEIGHT (KG)	PALLET DIMENSIONS L X W X H (CM)	APPROXIMATE NET WEIGHT (KG)
(cm)	L x W x H (cm)	300 g/ m2	450 g/m2	600 g/m2
130	120x120x147	702	738	702

- Number of rolls per pallet = 9 vertical - Pallet height is equal to mat width + 17 cm.
- The pallet is wrapped with polyamide straps.
- Special packaging: strips are packed in cardboard boxes of palletized according to the quantity.

LABELING

Each pallet has two identification labels detailing the product reference, the net and gross weights in Kg, packaging and product code, identification code of the palletized unit, production date.

STORAGE

The M113 mat should be stored in its original packaging in a dry and cool place. Best conditions are at temperature from 10 to 35°C and humidity between 35 and 85 %. If you store the product at lower temperatures, please move the soon to be processed pallets to the production area 24 hours ahead of time; remove part of the protective cover of each roll to prevent condensation. You can stock pallets one on one with a plywood plank in between the two.

Contact

ChoppedStrandMats.ocvamericas@owenscorning.com ChoppedStrandMats.ocvemea@owenscorning.com ChoppedStrandMats.ocvap@owenscorning.com



OCVTM Reinforcements

**OWENS CORNING
COMPOSITE MATERIALS, LLC**
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK®
www.owenscorning.com
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.**
166, CHAUSSÉE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

**OWENS CORNING - OCV ASIA PACIFIC
SHANGHAI REGIONAL HEADQUARTERS**
2F OLIVE LVO. MANSION
620 HUA SHAN ROAD
SHANGHAI 200040
CHINA
+86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.